## **()** LG Chem Data Sheet



Brackish Water Reverse Osmosis (RO) Membranes

LG BW 400 ES Energy Saving

## **Overview**

LG Chem's NanoH<sub>2</sub>O<sup>TM</sup> brackish water RO membranes serve various municipal and industrial applications and have been operating in the major utilities around the world. Incorporating innovative Thin Film Nanocomposite (TFN) technology, all LG BWRO membranes provide superior performance along with intrinsic anti-fouling property and are suitable for applications where consistent and reliable performance is a must.

LG BW ES membranes offer high permeability at low feed pressure, significantly reducing operating costs: suitable for low to medium salinity brackish water applications.

## **Product Specifications**

Active Membrane	Permeate flow rate, GPD (m <sup>3</sup> /d)	Stabilized Salt	Minimum Salt	Feed Spacer,
Area, ft² (m²)		Rejection, %	Rejection, %	mil
400 (37)	10,500 (39.7)	99.6	99.5	34*

Test Conditions : 2,000 ppm NaCl at 25°C (77°F), 150 psi (10.3 bar), pH 7, Recovery 15%. Permeate flows for individual elements may vary +/-15%.

\*Low dP spacer is available upon special request.

	A,	B,	C,	Weight,
	mm (in.)	mm (in.)	mm (in.)	kg (lbs.)
¥ [	1,016	200	28.6	16
	(40)	(7.9)	(1.125)	(35)

All dimensional information is indicative and for reference purpose only. Please contact LG Chem for detailed technical specification.

## **Operating Specifications**

For more information and operating guidelines, visit www.lgwatersolutions.com

Max. Applied pressure	600 psi (41 bar)	
Max. Chlorine concentration	< 0.1 ppm	
Max. Operating temperature	45°C (113°F)	
pH Range, Continuous (Cleaning)	2-11 (2-12)	
Max. Feedwater turbidity	1.0 NTU	
Max. Feedwater SDI (15 mins)	5.0	
Max. Feed flow	75 gpm (17 m <sup>3</sup> /h)	
Max. Pressure drop ( $\Delta P$ ) for each element	15 psi (1.0 bar)	

The information and data contained herein are deemed to be accurate and reliable and are offered in good faith, but without guarantee of performance. LG Chem assumes no liability for results obtained or damages incurred through the application of the information contained herein. Customer is responsible for determining whether the products and information presented herein are appropriate for the customer's use and for ensuring that customer's workplace and disposal practices are in compliance with applicable laws and other governmental enactments. Specifications subject to change without notice. NanoH<sub>2</sub>O is the Trademark of The LG Water Solutions or an affiliated company of LG Chem. All rights reserved. C LG Chem, Ltd.

Rev. M (09.27)